



Subham Oils and Resins Pvt Ltd

HO: Astra Tower, ASO 301, 3rd Floor, Action Area IIC, New Town, Kolkata-700161

Technical Data Sheet

TSA AC TS 101 60%

Applications: Domestic Appliances, low baked stoving for auto body

Specifications:

Parameters	Standard Results
Non Volatile Matter(%) @120 Deg C	60 +-2 %
Viscosity in Poise at 25C	10-20 Poise
Acid Value (mgKOH/gm)	Less than 15
Colour in Gardener	Water White

Delivery Forms:-

In 200 kgs in 17-18 kgs MS Drums in Xylene/Butanol solution